



# W3H32M64E-XSBX Construction & Qualification Quality and Reliability Report

## W3H32M64E-XSBX PACKAGE CONSTRUCTION + QUALIFICATION

### ENCAPSULANT

- The encapsulant is not injection molded to control wire sweep effects
- $T_G = 150^\circ\text{C}$
- Moisture sensitivity is to JEDEC level 3

### INTERPOSER MATERIAL

- CTE = 12-13 ppm / °C
- Water absorption = 0.13%

### BALLS

- Eutectic solder Sn63/Pb37
- Diameter = 0.60mm (0.024) NOM

### TEST

- Burn-In – 100%-48 hours at 125°C
- Final Electrical Test – 100% at maximum and minimum ambient temperatures

#### Temperature Ranges Available:

-55°C to +125°C

-40°C to +85°C

0°C to +70°C

### SHIPPING

- Final bake out
- Shipped in JEDEC standard trays and anti-static shielded dry pack bags
- Humidity indicator cards are included
- Desiccant used in dry packs

## QUALIFICATION INFORMATION

Qual for 208 PBGA Product					
Qual Test	# of Pieces	Duration	Reference Standards	Temp. Range	Results
Preconditioning	All Test Samples		EIA/JESD22 Method A113		Pass
Bias Life Test	15	1000 hrs.	EIA/JESD22 Method A108	125°C	15 Pass
Temperature Cycle	15	1000 cycles	EIA/JESD22 Method A104 Condition B	-55°C to +125°C	15 Pass
85/85 Bias	15	1000 hrs.	EIA/JESD22 Method 101	85°C	15 Pass

(200A00004-46)